

PROCESS FOR PREPARING CORROSION-RESISTANT
METAL ARTICLES FOR MARINE APPLICATIONS

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The present invention is directed to a process for preparing corrosion-resistant articles for marine use, and the products prepared by the process.

2. Background Art

10 Metal articles and structures are widely used in the marine field, particularly in pleasure craft, fishing boats, and the like. Unless stainless steel or certain marine bronzes are used to manufacture such articles, corrosion, with its associated aesthetic problems and failure modes can be expected to severely limit product lifetime. Even when these two relatively corrosion-resistant classes of materials are used, corrosion may still take place, particularly in salt water or
15 brackish environments. It is partially for this reason that pleasure boats operated in salt water have considerably lower resale value than similar vessels operated in fresh water.

 Corrosion problems are most severe when more active metals such as magnesium, aluminum, and carbon steel are used. Such items may become
20 severely corroded over relatively short periods of time in salt water environments.

 To lessen the corrosive effects on metals, it has been common to provide surface treatments. Chrome and nickel plating have been used, for example. However, plating is relatively expensive, particularly when large fabricated structures constructed by welding are to be plated. In addition, such
25 plating procedures do not work well on many active metals such as aluminum.

Anodizing has also been used to increase corrosion resistance, and is effectively used on small parts. However, large tubular structures such as radar arches are typically welded together. The anodized coating is destroyed locally during the welding process. Anodizing very large, prefabricated structures is not cost-effective.

Painting has long been used to provide corrosion resistance, and literally hundreds, if not thousands, of coating systems have been proposed. Powder coating systems, for example using epoxy-type powdered resins which are subsequently heat cured can produce excellent finishes. However, powder coating of large articles becomes expensive due to the size of the cure oven necessary. Moreover, powder coating systems exhibit the same corrosion deficiencies associated with other coatings.

Use of conventional, solvent-borne coatings is becoming increasingly difficult due to environmental legislation limiting emissions of volatile organic compounds (VOCs). Moreover, most such coatings do not provide the necessary levels of corrosion protection, and application to substrates involves a time and labor-extensive combination of primer application, smoothing filler, and topcoat application, with numerous sanding and smoothing steps in-between.

A problem with coatings subject to corrosion occurs when a prefabricated structure is altered to mount to non-standard surfaces or to mount additional components thereon. For example, flybridges and radar arches are often used to mount flag holders, GPS and RF antennae, hand holds, cleats, "rocket launcher" fishing pole receptacles, and the like. Drilling the necessary mounting holes into the coated structure penetrates the coating, exposing untreated metal to the environment. Corrosion rapidly occurs at such areas, frequently spreading between the coating and its metal substrate causing ultimate separation of the coating.

It would be desirable to provide a process by which metal (and non-metal) articles slated for marine use could be coated with a corrosion-resistant

coating employing a minimum of finishing steps. It would further be desirable to provide a coating which offers extended corrosion resistance even after having had bare metal exposed.

SUMMARY OF THE INVENTION

5 It has now been surprisingly discovered, that a two-part polyurethaneurea coating derived from a low viscosity isocyanate-terminated prepolymer and a mixture of diamine and hydroxyl-functional curing agents can be applied to marine products by conventional spraying techniques to produce a smooth, corrosion-resistant coating which maintains its corrosion resistance even
10 after exposure of bare metal to the environment by penetration of the coating, and even under salt spray conditions.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

 The process of the present invention involves coating marine articles with a two-part coating polyurethaneurea composition at elevated temperature, and
15 allowing the coating to cure to a corrosion-resistant film.

 The articles to be coated include both metal and non-metal articles to be used in marine environments. Preferably, the articles are metal items used as fittings and structures on watercraft. Non-limiting examples include cleats, plates, antennas, antenna mounts, radar arches, bow rails, rub rails, fishing pole holders, downrigger mounts, rails, stanchions, swim platform supports, exhaust ports, mast
20 bases, back stays, chain plates, transom, swim, and boarding ladders, tuna towers, fishing platforms, flybridges, anchors, anchor rollers, and the like. The metal substrate may be any metal, for example brass, bronze, bright metal, zinc, magnesium, aluminum, steel, stainless steel, and the like. Preferred are steel (non-stainless), stainless steel, chrome-plated metals, aluminum, and magnesium. Terms
25 such as aluminum, magnesium, bronze, etc. include the various alloys of these metals. Preferred non-metal substrates are thermoplastic sheet material and fiber-reinforced thermoset and fiber-reinforced thermoplastics. Fiber reinforcement of

the latter includes fiberglass, thermoplastic fiber, carbon fiber, ceramic fiber, etc., whether in the form of strands, tow, yarn, woven or non-woven products, felted products, and whether the fiber reinforcement is short fiber, long fiber, continuous fiber, etc.

5 The two-part polyurethaneurea coating is supplied in at least two components to a spray gun. Although it is possible to supply three or more components, it is simple and most economical to supply the components in what are conventionally termed "A-side" and "B-side" components, the A-side containing the isocyanate-functional components and the B-side containing the isocyanate-
10 reactive components.

Both the A-side and B-side desirably have viscosities which are below 500 cp at the spray temperature in order for sufficient mixing and atomization to take place. However, higher viscosities are possible provided suitable mixing and atomization can be achieved.

15 The components are preferably VOC-free. By VOC-free is meant that no added solvent is employed. The coating components are substantially 100% solids. However, it is possible to add minor amounts of solvent, particularly when component viscosity is higher than desired. In such cases, addition of up to 20 weight percent solvent, more preferably 10 weight percent or less, and most
20 preferably 5 weight percent or less of solvent may be practiced. When solvent is added, it is preferably that the solvent be a "zero-VOC" solvent, *i.e.*, a solvent which is not viewed as contributing to environmental problems. Such solvents are known, for example, in U.S. Patent 6,048,471. An example of such a solvent is *t*-butylacetate. Mixtures of such solvents may also be used.

25 The A-side of the polyurethaneurea coating is an isocyanate-terminated prepolymer prepared by reacting an excess of a diisocyanate with a difunctional polyoxyalkylene polyol. The isocyanate is in excess such that an NCO-group content of preferably from about 2 weight percent to about 12 weight percent, more preferably 4 weight percent to 8 weight percent is obtained. The

diisocyanates employed are preferably mononuclear cyclic diisocyanates such as isophorone diisocyanate or the toluene diisocyanates, preferably a commercial mixture of 2,4- and 2,6-toluene diisocyanates. While straight chain aliphatic isocyanates such as 1,6-hexane diisocyanate may also be used, their use is less preferred. Also less preferred are the polynuclear diisocyanates such as 2,4'-, 2,2'-, and 4,4'-methylene diphenylene diisocyanates. The preferred diisocyanates are an 80:20 blend of 2,4- and 2,6-toluene diisocyanate.

The polyol component employed to react with the isocyanate to form the A-side prepolymer is a 300 to 4000 Da average molecular weight hydrophobic polyoxyalkylene diol. The term "average molecular weight" as used herein is the molecular weight calculated from the polyol hydroxyl number assuming the theoretical functionality of the polyol, not its actual, measured functionality. By "hydrophobic" is meant that the polyol contains insufficient polyoxyethylene groups to provide substantially hydrophilic segments. Such an amount is 20 weight percent or less, preferably randomly distributed, with no more than 10 weight percent as an internal or external block. Preferably, the hydrophobic polyol contains no oxyethylene moieties.

Preferably, the hydrophobic polyol is a mixture of one or more polytetramethylene ether glycols (PTMEG) and/or low unsaturation polyoxypropylene diols with an unsaturation less than 0.010 meq/g polyol. The polyol component preferably has an average molecular weight between about 500 Da and 2000 Da, more preferably between 600 Da and 1000 Da. Most preferably, mixtures of two different hydrophobic polyols, generating a polyol blend having a bimodal molecular weight distribution is employed. Most preferably, a blend of 1000 Da and 650 Da PTMEG is used. The prepolymer is prepared by conventional prepolymer techniques, *i.e.*, by admixing the isocyanate and polyol components and heating, with or without catalyst, until the isocyanate group content stabilizes. Reference may be had to Saunders and Frisch, Polyurethanes, CHEMISTRY AND TECHNOLOGY, Wiley Interscience, New York.

Although the A-side is most preferably entirely difunctional, it would not depart from the spirit of the invention to include a small percentage, *i.e.*, 10 equivalent percent or less, based on the diol component, of a triol, tetrol or higher functional polyether, preferably 5 equivalent percent or less. Likewise, a tri- or higher functional isocyanate could be used in similar proportions. The presence of other than difunctional components generally increases coating hardness and solvent resistance, but at the expense of increased A-side viscosity and decreased elongation and flexibility. Thus, a two-functional A-side prepolymer is desired.

The B-side comprises a diamine and a polyol. The diamine is preferably a sterically hindered diamine such as diethyltoluene diamine, although other diamines such as 2,4-, 2,6-, and 3,5-toluene diamine, ethylene diamine, 1,6-diaminohexane, isophorone diamine, and the like may also be used. Bi- or polynuclear diamines such as 2,2'-, 2,4'-, and 4,4'-methylenedianiline may also be used.

The polyol components of the B-side may be the same polyols as used in the A-side prepolymer, although a mixture of polyols is not preferred. The polyol may preferably be a 200 Da to 4000 Da PTMEG or low unsaturation polyoxypropylene diol, more preferably 400 Da to 2000 Da. Most preferably, a polyoxypropylene diol is employed with diethyltoluene diamine (DETA) in a DETA/polyol weight ratio of about 2:1. The polyoxypropylene diol may be a low unsaturation diol.

The coating is preferably clear, although pigments may be added if desired. Suitable pigments include those commonly known, for example titanium dioxide, iron oxides, metal chromates, metal sulfides, and the like, as well as organic pigments of a wide range of chemical constitution and color. Preferably, no pigments are added. The coating may also contain conventional additives such as flow control agents, rheology modifiers, etc. However, it has been found that such are generally unnecessary.

It is also possible to employ the present coating composition as a base coat, and to spray a top coat, preferably a pigmented top coat, over the polyurethaneurea base coat. Primer coats are generally used, but are not always necessary. A preferred primer is NR-9500 primer, a two-part primer available from
5 Normac Adhesive Products, Inc., Burlington, Ontario, Canada. Primer thickness is generally rather thin, for example between 12.5 μm and 25 μm . The primer is generally applied to surfaces which have been cleaned and degreased by conventional methods.

It has been found that the coatings employed in the inventive process
10 provide a pleasing, aesthetic appearance without the expenditure of numerous man hours or priming, sanding, filling, and other steps. Unlike the majority of other coatings, it is also possible to provide a clear coat of the polyurethaneurea, optionally with underlying primer, whereas many competing products rely on heavy loadings of pigments and finely divided metals to provide corrosion resistance.

Upon drilling through a coating structure, it is still advisable to
15 employ a gel-like or grease-like protectant, *i.e.*, a teflon-containing protectant such as Tefgel™, available from Ultra Safety Systems, to cover exposed bare metal. This is especially so when fasteners of a different material are used, allowing the possibility of galvanic corrosion to occur between dissimilar metals. Teflon coated
20 stainless steel fasteners are recommended for the same reason. However, unlike other coatings which blister, crack, peel, or separate despite such precautions, the present coatings perform exceedingly well over long periods of time despite penetration of the polyurethaneurea coating down to the bare metal.

Particularly preferred A-side and B-side are those previously
25 described, and also those described in U.S. Patent 4,267,299, incorporated herein by reference. A particularly preferred system is NR-95LVHS plural component sprayable urethane, available from Normac Adhesive Products, Inc., Burlington, Ontario, Canada. This product is a TDI prepolymer of a mixture of 650 Da and 1000 Da PTMEG glycols (A-side) and a 2:1 by weight blend of DETA and
30 polyoxypropylene diol as the B-side.

The viscosity of the A and B components, particularly the A component, is generally rather high at room temperature, and thus it is preferred to heat the components prior to mixing and spraying to reduce their viscosity when necessary. The component(s) are preferably heated to a temperature where the most viscous of the two components has a viscosity of 500 cp or less. It is generally impractical to apply the coating at component temperatures in excess of 200° F, and temperatures below 180° F are preferred. With the preferred system, spraying temperatures of 150-160° F have proven practical.

Conventional spray equipment suitable for handling heated components may be used for application. The A and B sides are supplied from separate pails, drums, or tanks, and are heated in line prior to being mixed when the component(s) viscosity warrants. Mixing may take place prior to the spray head by mechanical or static mixing, *i.e.*, by an in line static mixer, or may take place in the spray head itself. The A and B ratios can be adjusted to provide the desired NCO/OH ratio. An NCO/OH ratio of 0.85 to 1.15 is preferably used, more preferably 0.90 to 1.10, and most preferably 0.95 to 1.05. The latter ratio has proven to be very satisfactory. With the most preferred system, the A-side is supplied in a 2:1 volume ratio with the B-side.

A preferred spray application system is the TBM spray system available from Normac Adhesive Products, Inc. This system employs a heated A-side with both static mixing as well as impingement mixing, along with individual piston-type pumps for the respective sides to eliminate ratio variances due to viscosity changes. The spray gun is the Probler gun manufactured by Glass Craft, with an adapter to fit Graco RAC IV spray tips.

When a primer coat is utilized, the polyurethaneurea coating is preferably applied within a time frame of 1 to 24 hours. The polyurethaneurea coating is generally applied in a thickness of minimally 10 mil, and as high as 500 mil or higher. It is noted that the polyurethaneurea has substantial strength and modulus, and therefore decreased part weight can be employed, compensating by employing a thicker polyurethaneurea coating. The coating is typically applied at

1 a thickness of 10 to 60 mil, preferably 20 to 40 mil per coat, with additional coats
2 used to supply the total coating thickness desired. Additional coats are preferably
3 applied prior to complete cure of the previous coating, in particular within two
4 hours from application of the first coat. If this preferred application window is
5 missed, further treatment of the prior coating surface, *i.e.*, sanding, steel wooling,
6 grit blasting, solvent-treating, etc., may be necessary for full adhesion.

7
8
9
10 The present invention also pertains to marine structures having a
11 metal frame, a thin surface of plastic or fiber-reinforced polymer over the frame,
12 and a substantial layer, *i.e.*, preferably from 100 to 200 mil or higher of a
13 polyurethaneurea coating which provides form-holding capability to the structure,
14 *i.e.*, supplies a considerable portion of the overall rigidity of the structure.
15 Substructures of aluminum and thin plastic film of a thickness similar to that of
16 shrink wrap may be coated to form a substantial structure by this process, for
17 example.

18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
218

The extreme resistance of the subject coatings to corrosion is exceptionally unexpected and surprising, particularly with respect to the numerous competitive coatings which were examined and which failed to provide adequate corrosion resistance.

- 5 While embodiments of the invention have been illustrated and described, it is not intended that these embodiments illustrate and describe all possible forms of the invention. Rather, the words used in the specification are words of description rather than limitation, and it is understood that various changes may be made without departing from the spirit and scope of the invention.